

ANCHOR MORTAR

E1 ANCHOR MORTAR
E1SF ANCHOR MORTAR

TEST CERTIFICATES AND SUPPORTING DOCUMENTS

- › Product acc. to DIN EN 15.04-6 "Anchoring of reinforcing bars" (E1)
- › High frost-deicing salt resistance - Verification by CDF procedure (E1)
- › Factory production control acc. to DIN EN 1504-6
- › Company certification acc. to DIN EN ISO 9001:2015

PROPERTIES

- › High flowability (E1)
- › Soft-plastic consistency (E1SF)
- › Controlled swelling with frictional bond
- › High early and final strengths and high bond stress
- › Low w/c value
- › Largely resistant to mineral oils and fuels
- › Complies with the requirements of building material class A1 (non-combustible) as specified under decision 2000/605/EC of the European Commission dated September 26, 2000 (published in the official journal L258)

AREAS OF APPLICATION

- › Sewage treatment plants
- › Grouting and casting of anchorings in solid rock, soil, concrete and masonry (E1)
- › For works overhead and for filling up joints, cavities and rock bolts (E1SF)
- › On vertical surfaces as well as for the centrifugal coating of pipes and shafts E1SF has to be used

MOISTURE CLASSES BASED ON CONCRETE CORROSION FROM ALKALI-SILICIC ACID REACTIONS

Moisture class	WO	WF	WA	WS
E1	•	•	•	•
E1SF	•	•	•	•

The aggregates in PAGEL®'s products comply with the requirements of alkali sensitivity class E1 from non-hazardous sources specified under DIN EN 12620.

EXPOSURE CLASS ALLOCATION ACC. TO: DIN EN 206-1 / DIN 1045-2

	XO	XC	XD	XS	XF	XA*	XM
		1234	123	123	1234	123**	123
E1	•	•••••	•••••	•••••	•••••	•••••	•
E1SF	•	•••••	•••••	•••••	•••••	•••••	•

* Having sulfate attack up to 1.500 mg/l

** With protective measures according to DIN 1045-2

TECHNICAL DATA

TYPE			E1	E1SF
Grain size		mm	0-0.5	0-0.5
Amount of water		%	30	13
Slump flow	5 min	mm	≥ 700	n. d.
	30 min	mm	≥ 600	n. d.
Measure of extension DIN EN 13395-1	5 min	mm	n. d.	150-190
Consumption (dry mortar) approx.		kg/m ³	1,600	1,800
Fresh mortar raw density approx.		kg/m ³	2,050	2,000
Processing time approx.	+ 20 °C	min	45	45
Swelling	24 h	Vol.-%	≥ 0.1	≥ 0.1
Compressive strength*	1 d	N/mm ²	≥ 40	≥ 15
	7 d	N/mm ²	≥ 55	≥ 40
	28 d	N/mm ²	≥ 65	≥ 50
Bending tensile strength*	1 d	N/mm ²	≥ 5	≥ 4
	7 d	N/mm ²	≥ 6	≥ 6
	28 d	N/mm ²	≥ 7	≥ 7

* Testing of bending tensile and compressive strength in accordance with DIN EN 196-1
n. d.: not determined

Note: All stated test values correspond to the DAfStb VeBMR directive.

Testing of fresh and solid mortars at 20 °C ± 2 °C, storage of the test specimen after 24 hours until the strength test in water at 20 °C ± 2 °C. Higher or lower temperatures result in deviating properties of fresh respectively solid mortars and test results. Depending on the temperature, the consistency can be adapted with a slight reduction of the mixing water.

Storage: 12 months. Cool, dry, free from frost. Unopened in its original container.

Delivery form: **E1:** 20-kg bag, Euro palette 960 kg

E1SF: 25-kg bag, Euro pallet 1,000 kg

Hazard class: Non-hazardous material, observe information on packaging.

PAGEL® PRODUCT COMPOSITION:

Cement: acc. to DIN EN 197-1

Aggregate: acc. to DIN EN 12620

Additions: acc. to DIN EN 450, general building inspection approval (abZ), DIN EN 13263
(fly ash, microsilica, etc.)

Admixtures: acc. to DIN EN 934-4

PROCESSING

SUBSTRATE PREPARATION:

Remove loose and unsound material such as cement slurry and dirt etc. using suitable methods, e.g. shot-blasting or similar until the underlying solid grain structure has been exposed. A sufficient average tear strength ($\geq 1.5 \text{ N/mm}^2$, $\text{KEW} \geq 1.0 \text{ N/mm}^2$) must be ensured.

Prewetting:

Prewet the concrete substrate to capillary saturation for approx. 6-24 hours.

Reinforced concrete:

The grade of surface preparation of reinforcement as well as other metallic parts is based on the requirements of the current applicable regulations and must be ensured before the application.

Non-iron metals:

Cement and cement-bound building materials may cause non-iron-metals in the transitional area of the contact surface (e.g. aluminium, copper, zinc) to loosen. Please contact us for technical advice.

FORMWORK:

Attach in such a way that it is leak-proof and robust. Seal on the concrete substrate. Use non-absorbent formwork.

Protruding grout:

Do not exceed the specified 50 mm when allowing grout to protrude and observe the structural specifications. When grouting dynamically stressed and prestressed base plates and machine foundations that are subject to high compression strengths at the edges, the grout should ideally be applied to be flush with the bearing plate, provided with a 45° edge using formwork or cut off flush with the bearing plate before it has set. This will prevent any stresses from becoming superimposed on one another and from becoming annihilated (observe static and structural specifications).

MIXING:

The dry mortar is supplied ready to use and only needs to be mixed with water. Fill the specified amount of water apart from a residual amount into a clean and suitable mixing device (e.g. compulsory mixer). Add the dry mortar and mix for at least 3 minutes. Add the remaining water and mix for at least another 2 minutes until it forms a homogeneous mass.

Mixing water:

Drinking water quality

Temperature range:

+5 °C to +35 °C

Low temperatures and cold mixing water reduce strength development, require intensive forced mixing and reduce flowability. Higher temperatures accelerate strength development and can also reduce the flowability.

GROUTING:

The mixture must be poured from one side or corner only in one continuous pour. When grouting large areas, we recommend to pour the grout starting in the centre of the foundation plate, using a funnel or filling hose. Cavities should be filled first (up to around just below the top edge) and then the machine plate or similar.

FOLLOW-UP TREATMENT:

Exposed grout areas must be protected from premature water evaporation (from wind, draughts, direct exposure to sun, etc.) immediately on completion of the work for a period of 3-5 days.

Suitable curing methods:

Water spray, foil covers with jute sheets, thermofolios or moisture-retaining covering sheets, **O1** Evaporation protection.

The technical data sheet must be observed when using **O1** Evaporation protection.